

## **DATA SHEET**

CERAMIC FIBER BULKHP	
Classification Temperature (℃)	1260
Working Temperature (°ℂ)	1100
Color	White
Short Content (%)	<15
Chemical Composition (%)	
$AI_2O_3$	45-46
$Al_2O_3$ + $SiO_2$	99
Fe <sub>2</sub> O <sub>3</sub>	<0.3
K <sub>2</sub> O+Na <sub>2</sub> O	<0.3

Note: Technical Data are typical results from test pieces. This information, subject to change, is offered solely for your consideration. Users of our products should make their own tests to determine the suitability of each product for their particular purposes.

ADD : FLOOR 17TH, NO. 4 BUILDING, ZHUYU
INTERNATIONAL COMMERCIAL CENTER NO. 9 SHOUTI
SOUTH ROAD, HAIDIAN DISTRICT, BEIJING CHINA.
POSTCODE: 100044