

DATA SHEET

CERAMIC FIBER BULKHA	
Classification Temperature (℃)	1350
Working Temperature (℃)	1200
Color	White
Short Content (%)	<15
Chemical Composition (%)	
Al_2O_3	53-55
Al ₂ O ₃ + SiO ₂	99
Fe ₂ O ₃	<0.2
K ₂ O+Na ₂ O	<0.2
CaO + MgO	<0.2

Note: Technical Data are typical results from test pieces. This information, subject to change, is offered solely for your consideration. Users of our products should make their own tests to determine the suitability of each product for their particular purposes.

ADD : FLOOR 17TH, NO. 4 BUILDING, ZHUYU INTERNATIONAL COMMERCIAL CENTER NO. 9 SHOUTI SOUTH ROAD, HAIDIAN DISTRICT, BEIJING CHINA.

POSTCODE: 100044