

## DATA SHEET

### ZIRCON-MULLITE BRICK--ZMS-26

#### Chemical Composition (%)

Al<sub>2</sub>O<sub>3</sub> ≥36

SiO<sub>2</sub> ≤30

Fe<sub>2</sub>O<sub>3</sub> ≤0.3

ZrO<sub>2</sub> ≥26

Bulk Density (g/cm<sup>3</sup>) ≥2.8

Apparent Porosity (%) ≤22

Refractoriness Under Load (T0.6)(°C) ≥1580

Note: Technical Data are typical results from test pieces. This information, subject to change, is offered solely for your consideration. Users of our products should make their own tests to determine the suitability of each product for their particular purposes.