

DATA SHEET

SILLIMANITE BRICKMS-60P	
Chemical Composition (%)	
AI_2O_3	≥60
SiO ₂	≤37
Fe ₂ O ₃	≤1.2
Bulk Density (g/cm³)	≥2.45
Apparent Porosity (%)	≤18
Cold Crushing Strength (Mpa)	≥70
Permanent Linear Change (1400°C×3h)(%)	±0.2
Refractoriness Under Load (T0.6)(℃)	≥1580

Note: Technical Data are typical results from test pieces. This information, subject to change, is offered solely for your consideration. Users of our products should make their own tests to determine the suitability of each product for their particular purposes.

TEL: 010 6879 6888 FAX: 010 6879 6668 WEBSITE: www.thermalcmax.com

ADD : FLOOR 17TH, NO. 4 BUILDING, ZHUYU INTERNATIONAL COMMERCIAL CENTER NO. 9 SHOUTI SOUTH ROAD, HAIDIAN DISTRICT, BEIJING CHINA. POSTCODE: 100044