



DATA SHEET

ITEM	S-94	S-95A	S-95B
SiO _{2,} %	≥94	≥95	≥95
Fe ₂ O ₃ , %	≤1.5	≤0.5	≤1
Residual Quartz, %	≤1	≤1	≤1
Apparent Porosity, %	≤23	≤24	≤23
Cold Crushing Strength, Mpa	≥29.4	≥27	≥20
Refractoriness Under Load $(T_{0.6})$, $^{\circ}\mathbb{C}$	-	≥1650	≥1600
Permanent Lineat Change, %	-	-	1500℃×4h, ±0.2

Note: Technical Data are typical results from test pieces. This information, subject to change, is offered solely for your consideration. Users of our products should make their own tests to determine the suitability of each product for their particular purposes.

TEL: 010 6879 6888

FAX: 010 6879 6668

WEBSITE: www.thermalcmax.com

ADD : FLOOR 17TH, NO. 4 BUILDING, ZHUYU
INTERNATIONAL COMMERCIAL CENTER NO. 9 SHOUTI
SOUTH ROAD, HAIDIAN DISTRICT, BEIJING CHINA.
POSTCODE: 100044