

ITEM	MZ-12A	MZ-12B	MZ-12C
MgO, %	≥75	≥72	≥72
SiO <sub>2</sub> , %	≤8	≤9	≤9
ZrO <sub>2</sub> , %	≥12	≥10	≥10
Apparent Porosity, %	≤15	≤16	≤17
Cold Crushing Strength, Mpa	≥60	≥50	≥45
Refractoriness Under Load (T <sub>0.6</sub> ), ℃	≥1680	≥1640	≥1620

## DATA SHEET

Note: Technical Data are typical results from test pieces. This information, subject to change, is offered solely for your consideration. Users of our products should make their own tests to determine the suitability of each product for their particular purposes.