

DATA SHEET

HIGH ALUMINA BRICK---ALP80

Refractoriness (°C)	1810
Apparent Porosity (%)	≤18
Cold Crushing Strength (Mpa)	≥100
Refractoriness Under Load (T0.6) (°C)	1550
Reheating Linear Change (%)	1550℃×2h -0.5 ~+0.5
Chemical Composition (%)	
Al ₂ O ₃	≥82

Note: Technical Data are typical results from test pieces. This information, subject to change, is offered solely for your consideration. Users of our products should make their own tests to determine the suitability of each product for their particular purposes.