

DATA SHEET

HIGH ALUMINA BRICK---UAL60

Refractoriness (°C)	1790
Bulk Density (g/cm ³)	≥2.35
Apparent Porosity (%)	≤20
Cold Crushing Strength (Mpa)	≥55
Refractories Under Load (0.2Mpa)	1450
Permanent Liner Change (%)	1500℃ × 2h
	0.1 ~-0.4
Chemical Composition (%)	
Al ₂ O ₃	≥60
Fe ₂ O ₃	≤1.5

Note: Technical Data are typical results from test pieces. This information, subject to change, is offered solely for your consideration. Users of our products should make their own tests to determine the suitability of each product for their particular purposes.